

## Silver Brazing Alloy J33100

Composition (wt %)									ISO 17672	AWS
Ag	Cu	Zn	Mn	Ni	Sn	Si	P	Altro		
33	33,5	33,5	-	-	-	-	-	-	-	-

### Technical data

Density	9 g/ cm <sup>3</sup>
Melting range	680-750 °C
Shear strength	-
Tensile strength	550 N/mm <sup>2</sup>
Recommended joint gap	0,05-0,2 mm
Maximum operating temperature of brazed joint	-

### Applications

Silver brazing alloy for general purposes with good flow properties. Joints generally present a very good tensile strength. However, joint strength depends on various factors: type of base metals to be joined, type of joint, joint gap, etc.

Heat sources commonly employed are flame or induction heating system.

### Standard forms and dimensions

Product	Feasibility
Wire	✓
Strip	✓
Rods	✓
Flux coated rods	-
Rings	✓

### Recommended fluxes

Universal FPA, General FPO, Special FPA.

### Note

Silver brazing alloys and dimensions other than those listed in our catalogue are available upon request.

Details included in this technical data sheets are based on our knowledge and experience and are believed to be accurate. All data in this data sheet are merely recommendations and shall not be regarded as an assurance of any properties of the product. *We do not assume any responsibility and make no warranty with respect to the results that may be obtained and the damages that may occur from the use of the information provided.*