

Silver Brazing Alloy J6010S

Composition (wt %)									ISO 17672	AWS
Ag	Cu	Zn	Mn	Ni	Sn	Si	P	Altro		
60	30	-	-	-	10	-	-	-	Ag 160	BAG-18

Technical data

Density	9,8 g/cm ³
Melting range	600-730 °C
Shear strength	-
Tensile strength	480 N/mm ²
Recommended joint gap	0,05-0,20 mm
Maximum operating temperature of brazed joint	200 °C

Applications

Silver brazing alloy with good flow properties, especially suitable for brazing stainless steel components. Joints generally present a very good tensile strength. However, joint strength depends on various factors: type of base metals to be joined, type of joint, joint gap, etc. Heat sources commonly employed are flame or induction heating system. The absence of zinc in the composition makes this alloy suitable for vacuum furnaces and for brazing under protected atmosphere.

Standard forms and dimensions

Product	Feasibility
Wire	✓
Strip	-
Rods	✓
Flux coated rods	-
Rings	✓

Recommended fluxes

Universal FPA, Universal FPO, Special FPA.

Note

Silver brazing alloys and dimensions other than those listed in our catalogue are available upon request.

Details included in this technical data sheets are based on our knowledge and experience and are believed to be accurate. All data in this data sheet are merely recommendations and shall not be regarded as an assurance of any properties of the product. *We do not assume any responsibility* and make *no warranty* with respect to the *results* that may be *obtained* and the damages that may occur from the use of the information provided.

Since end use of the product is not under our direct control, it is the user's responsibility to comply with applicable safety and hygiene laws and regulations.